



# Figure of Merit Characteristics Compared to Engineering Parameters

*C.M. Schrader*  
*BAE Systems, Huntsville, Alabama*

*D.L. Rickman*  
*Marshall Space Flight Center, Marshall Space Flight Center, Alabama*

## The NASA STI Program...in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the lead center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.
- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and mission, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized databases, organizing and publishing research results...even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI program home page at <<http://www.sti.nasa.gov>>
- E-mail your question via the Internet to <[help@sti.nasa.gov](mailto:help@sti.nasa.gov)>
- Fax your question to the NASA STI Help Desk at 443-757-5803
- Phone the NASA STI Help Desk at 443-757-5802
- Write to:  
NASA STI Help Desk  
NASA Center for AeroSpace Information  
7115 Standard Drive  
Hanover, MD 21076-1320

NASA/TM—2010–216443



# Figure of Merit Characteristics Compared to Engineering Parameters

*C.M. Schrader*  
*BAE Systems, Huntsville, Alabama*

*D.L. Rickman*  
*Marshall Space Flight Center, Marshall Space Flight Center, Alabama*

National Aeronautics and  
Space Administration

Marshall Space Flight Center • MSFC, Alabama 35812

---

*September 2010*

Available from:

NASA Center for AeroSpace Information  
7115 Standard Drive  
Hanover, MD 21076-1320  
443-757-5802

This report is also available in electronic form at  
<<https://www2.sti.nasa.gov>>

## TABLE OF CONTENTS

1. INTRODUCTION .....	1
1.1 2005 Regolith Simulant Workshop .....	1
1.2 Development of Figures of Merit .....	1
1.3 Explanation of the 2005 Workshop Rankings With the Figure of Merit .....	2
2. FIGURE OF MERIT .....	3
2.1 Objective of Figure of Merit .....	3
2.2 Parameters .....	3
3. EVALUATION OF RECOMMENDED PROPERTIES VERSUS FIGURE OF MERIT .....	5
3.1 Geomechanical (Mechanical Strength Properties) .....	7
3.2 Physical .....	8
3.3 Grain Specific .....	9
3.4 Chemical .....	10
3.5 Mineralogical .....	11
3.6 Multicategory .....	12
4. CONCLUSION .....	13
REFERENCES .....	15



## LIST OF TABLES

1.	Properties from the 2005 Lunar Simulant Workshop, from table 2 in Sibille et al. ....	5
2.	Properties from 2005 workshop correlated to FoM properties by which they are directly addressed or from which they are derived .....	6



## LIST OF ACRONYMS

Br	bromine
Cl	chlorine
CO <sub>2</sub>	carbon dioxide
F	fluorine
Fe <sup>0</sup>	iron metal
FoM	figure of merit
H <sub>2</sub> O	water
I	iodine
ISRU	in situ resource utilization
MSFC	Marshall Space Flight Center
nFe <sup>0</sup>	nanophase iron metal
OH	hydroxyl
P	phosphorous
TM	Technical Memorandum



## TECHNICAL MEMORANDUM

### FIGURE OF MERIT CHARACTERISTICS COMPARED TO ENGINEERING PARAMETERS

#### 1. INTRODUCTION

Current NASA lunar architecture calls for permanent human habitation of the Moon by the year 2020. Due to the expense of delivering materials into orbit, technologies are being developed to use lunar regolith for building and as a material resource for fabrication, oxygen production, and other needs. Additionally, constant exposure to the finest size fraction of lunar regolith may present hazards to human health. Towards developing these technologies and mitigating hazards, lunar regolith simulants are becoming an increasingly important part of the development paradigm.

##### 1.1 2005 Regolith Simulant Workshop

In January 2005, Marshall Space Flight Center (MSFC) hosted a workshop in Huntsville, AL, to discuss the future development of lunar regolith simulants. This meeting brought together geoscientists including some major figures in lunar geology, project managers, engineers, and simulant users from NASA centers, academia, and private enterprise. In addition to 2 days of presentations (content is available at < [http://est.msfc.nasa.gov/workshops/lrsm2005\\_program.html](http://est.msfc.nasa.gov/workshops/lrsm2005_program.html) >), sessions were held to identify characteristics necessary for a lunar regolith simulant to sufficiently serve the community. Regolith characteristics were discussed and votes were taken with regard to perceived importance. Following the 2005 workshop, Sibille et al. published a technical paper ranking these properties.<sup>1</sup>

##### 1.2 Development of Figures of Merit

Between 2005 and 2007, the lunar regolith simulant project advanced considerably. Much of the progress and development is evident in presentations of the October 2007 MSFC-hosted Huntsville workshop < [http://isru.msfc.nasa.gov/2007wksp\\_docs.html](http://isru.msfc.nasa.gov/2007wksp_docs.html) >. Part of the evolution was the establishment of the figure of merit (FoM) mathematics and algorithm for formal, quantitative comparison of two particulate materials composed of geologic components.<sup>2,3</sup> Although normally the comparison will be between a particular sample of lunar regolith and a simulant, the FoM can also be used to compare two simulants or two regolith samples.

### **1.3 Explanation of the 2005 Workshop Rankings With the Figure of Merit**

The primary motivation for this document is to define the relationship between the four FoM measurements and other characteristics of interest. For the most part, it is shown that the characteristics of interest from the 2005 conference are either directly contained within one of the four attributes measured for and evaluated by the FoM, or they are derivative characteristics resulting from one or a combination of the FoM attributes. This information is presented along with a brief explanation in cases where the ranked characteristics from the 2005 workshop are not measurable, technically undefined, or not addressed by the FoM.

## **2. FIGURE OF MERIT**

### **2.1 Objective of Figure of Merit**

The FoM was designed as a practical and efficient way to characterize and compare materials. Towards this end, the parameters for evaluation are chosen to have the following characteristics:

- **Definable:** Many characteristics of materials are not rigorously defined. This is true even of some important physical characteristics like surface activation.
- **Measurable:** Parameters were chosen that could be measured economically, in a timely fashion, and with results reproducible across laboratories.
- **Useful:** For simplicity of design, parameters were chosen that correlate to properties important to the functioning of simulant under expected conditions.
- **Primary versus derivative:** This concept recurs throughout the FoM logic. Some characteristics are inherent to a material, like the composition of its constituents, be they minerals or glass. All else being equal, other properties, like the behavior of a material during heating, are derivative of the composition.

These are positive attributes desirable in any standard.

Expressed in the negative, if something cannot be rigorously defined and measured reproducibly by multiple people, it has little value in a standard. If it cannot be practically known, a problem common with lunar materials for a host of reasons, it is not of functional utility within a standard. If a variable cannot be realistically measured in a way suitable for controlling the manufacture and the use of simulants, it has little place in a standard. If a parameter does not discriminate between materials, it has limited function to a quantitative standard.

### **2.2 Parameters**

The FoM requires four types of measurements from both the reference material and the simulant: Particle type, particle size, particle shape, and density. These four material attributes were chosen to comply with the above objectives and because they are measurable quantities from which almost all of the 31 characteristics ranked during the 2005 conference are derived. They also are functionally useful to anyone seeking materials to make simulant, to those trying to manufacture simulant, and to those trying to use the simulant. Refer to reference 3 for a formal definition of the four characteristics.

#### **2.2.1 Particle Type/Composition**

Composition describes attributes of a particle that exist without regard to size or shape. Here, the term particle is used to mean a piece of solid matter mechanically separable from others, such as by use of a sieve. The 2005 report uses the term grain for several basic concepts. This

is common practice for geologists who, by training and experience, understand the meaning by context. Because the majority of simulant users and developers are not geologists, the simulant development project explicitly decided to restrict grain to mean a discrete subset of a particle. All particles in lunar regolith or simulant will be comprised of glass and/or mineral grains, but particles may be amalgams of grains that result in lithic fragments (rock particles) or agglutinates.

Therefore, the first order of classification of constituents includes mineral grains, glass grains, lithic fragments, and agglutinates. Measuring proportions of particle types by volume is known in geologic science as a modal analysis and is usually reported in modal percent by each constituent. Although it is not required by the FoM, it is ideal that modal analyses be obtained for a material in several different size fractions. This is because the percentages of constituents of any bulk material will tend to vary by size due to differential susceptibility to grinding and crushing. Modal analyses for lunar highlands regolith have been published (e.g., reference 4). These data serve as the basis for the regolith simulant team's reference material in the FoM algorithm, but more precise data are being gathered to augment them.

### **2.2.2 Particle Size Distribution**

For the FoM, particle size is measured on a particle-by-particle basis and reported as a distribution. The number of bins and the size of the bins are defined by the user, but a more precise FoM evaluation is rendered by an approximation to the lunar regolith dataset. For instance, these data can be found in The Lunar Soils Grain Size Catalog.<sup>5</sup>

### **2.2.3 Particle Shape Distribution**

Particle shape is a crucial parameter in determining many geotechnical properties such as abrasiveness and bulk shear strength. The FoM calls for measurement of shape on a particle-by-particle basis, which is then reported as a distribution. Shape is described by two parameters, aspect ratio and sphericity. The specific algorithms for measuring these characteristics are being determined.

### **2.2.4 Density**

Density as an FoM parameter refers to bulk density, and it is the only parameter that is not measured by the particle but as a bulk characteristic. The measurements that comprise the density FoM are minimum bulk density, maximum bulk density, and specific gravity. Measured as such, the bulk density FoM conveys information as to the specific gravity of the constituent particles and on the packing (i.e., the bulk relationship of the particles to one another). It is the FoM property most easily affected by handling of the simulant.

### 3. EVALUATION OF RECOMMENDED PROPERTIES VERSUS FIGURE OF MERIT

Table 1 contains the ranked properties from the 2005 workshop. It should be noted that neither rigorous definitions of these properties nor suggested measurement protocols or standards were provided.

Table 1. Properties from the 2005 Lunar Simulant Workshop, from table 2 in Sibille et al.<sup>1</sup>

Category		Category Properties Listing	
		Regolith Property	Rank
Geochemical (metered strength properties)		Compressive strength	10
Total number of ranked properties	11	Coefficient of friction	12
Number of properties in top 10	1	Shear strength	18
		Hardness	23
		Rheology	24
		Angle of repose	25
		Tensile strength	27
		Fracture behavior	28
		Impact resistance	32
Physical		Particle density	3
Total number of ranked properties	7	Bulk density	5
Number of properties in top 10	2	Porosity	13
		Thermal properties	20
		Surface area	21
		Friability	22
		Permeability	26
Grain specific		Grain size	1
Total number of ranked properties	6	Grain size distribution	2
Number of properties in top 10	4	Grain shape	7
		Magnetic grain properties	9
		Grain shape distribution	16
		Electrostatic charging	17
Chemical		Glass composition	4
Total number of ranked properties	6	Bulk chemistry	8
Number of properties in top 10	4	Reactivity as volatile/soluble minerals	14
		Surface reactivity (including damage)	29
Mineralogical		Mineralogical composition as function of grain size	6
Total number of ranked properties	4	Modal mineralogical composition	11
Number of properties in top 10	2	Soil texture	30
Multicategory		Implanted solar particles	15
Total number of ranked properties	2	Agglutinates with nanophase iron metal (nFe <sup>0</sup> )	31
Number of properties in top 10	0		

The 2005 report uses the term grain for several basic concepts. The simulant development project has subsequently decided to explicitly restrict grain to mean a discrete subset of a particle.

In concept, a particle is a physically isolatable mass not chemically bonded to anything else. The grain commonly is a crystal of a mineral, but it can also be a piece of glass.

Table 2 presents relationships of properties to the FoM. Comments are provided for each parameter that is not explicitly a part of the FoM standard. In most cases the comments indicate the basic science explaining how the property is a derivative property. Also, where there are limitations to the assumptions or assertions made, some consideration of the limitations is given.

Table 2. Properties from 2005 workshop correlated to FoM properties by which they are directly addressed or from which they are derived.

Category Properties Listing Regolith Property	Particle Type	Particle Size Distribution	Particle Shape Distribution	Density	Not Addressed or Undefined
Compressive strength					
Coefficient of friction					
Shear strength					
Hardness					
Rheology					
Angle of repose					
Tensile strength					X
Fracture behavior					
Impact resistance					
Particle density					
Bulk density					
Porosity					
Thermal properties					
Surface area					
Friability					
Permeability					
Grain size					
Grain size distribution					
Grain shape					
Grain shape distribution					
Magnetic grain properties					
Electrostatic charging					
Glass composition					
Bulk chemistry					
Reactivity as volatile/soluble minerals					X
Surface reactivity					X
Mineralogical composition as function of grain size					
Modal mineralogical composition					
Soil texture					X
Implanted solar particles					X
Agglutinates with nFe <sup>0</sup>					

Notes:

	Property directly addressed by FoM
	Property derivative of FoM property
	Property partially dependent on environment

## **3.1 Geomechanical (Mechanical Strength Properties)**

### **3.1.1 Compressive Strength**

This is a derivative property. It is a function of the particles' composition, size, shape, and how they are packed together. To the limit the FoM parameters can be measured in both the simulant and the lunar material, this property is tightly constrained by the FoM.

### **3.1.2 Coefficient of Friction**

This is a derivative property. It is a function of the particles' composition, size, shape, and packing. To the limit the FoM parameters can be measured in both the simulant and the lunar material, this property is tightly constrained by the FoM.

### **3.1.3 Shear Strength**

This is a derivative property. It is a function of the particles' composition, size, shape, and how they are packed together. To the limit the FoM parameters can be measured in both the simulant and the lunar material, this property is tightly constrained by the FoM.

### **3.1.4 Hardness**

Hardness, as a geomechanical property, is ambiguous or undefined at best. In the 2005 workshop report, the context of usage is always with respect to a single particle. In the report, the usage is also with either the explicit statement or the assumption of mineral hardness as used by geologists. Assuming this is the intention of the term, the FoM particle type very tightly constrains this property. The limitation is the mechanical strength of lithic fragments and shattered particles. For this small minority of particles, the basic concept breaks down. In engineering, applications terms such as abrasiveness are substituted.

### **3.1.5 Rheology**

Rheology is the branch of physics that deals with the deformation and flow of matter, especially the non-Newtonian flow of liquids and the plastic flow of solids. As used in the 2005 workshop report, "The rheological behavior (flow properties) of the regolith is a key property of the bulk material during excavation." The particle size and shape distribution and the bulk density largely determine the flow properties of a material.

### **3.1.6 Angle of Repose**

The rheological behavior (flow properties) of the regolith is a key property of the bulk material during excavation. As an example, it manifests itself in the angle of repose of a regolith slope forming a trench or an erected berm. See section 3.1.5 of this Technical Memorandum (TM).

### **3.1.7 Tensile Strength**

The varying types of tensile strength describe a material's reaction to stress and are defined as the maximum stress before rupture (breaking strength) or deformation (yield strength). The tensile strength of an individual particle is entirely constrained by the composition of the particle, although the properties may not have been adequately measured for some composite particles like breccias and agglutinates. Tensile strength of the bulk material is less well defined, but it should be a derivative of all of the four FoM characteristics.

### **3.1.8 Fracture Behavior**

Fracture behavior of particles is driven by the particle type, specifically the hardness, cleavage, and fracture properties inherent in mineral and glass. These are addressed by the FoM and to some extent by particle shape. Whether and how particles fracture in bulk material, as a response to stress, is dependent on their size and packing.

### **3.1.9 Impact Resistance**

Impact resistance should be akin to fracture behavior (section 3.1.8 of this TM).

## **3.2 Physical**

### **3.2.1 Particle Density**

If the particle type is known, this can be directly computed to high or very high precision. The limitation is for particles with large amounts of internal voids such as agglutinates and, to a lesser extent, shattered particles. The significance of this error for a bulk sample is estimated to be much less than 1%. For individual particles, it is estimated to be as high as 20%.

### **3.2.2 Bulk Density**

This is an explicit part of the FoM standard. However, it is not rigorously defined in the 2005 recommendations.

### **3.2.3 Porosity**

Porosity is a function of the particle type (due to vugs and voids in particles), shape and size distribution, and bulk density. It may not be uniquely constrained by these characteristics.

### **3.2.4 Thermal Properties**

Thermal properties are derivatives of the particle type, size and shape distribution, and bulk density. Particles will have distinct conductive/insulating properties and the contact relationships between them will depend on size, shape, and bulk density.

### **3.2.5 Surface Area**

Surface area is a function of particle size and shape distribution, and its bulk density will determine the surface area exposed in a given volume of material. Surface area is uniquely constrained by these parameters, but effective surface area defined as surface area available for contact is more largely dependent on the type of packing that may not be uniquely described by the bulk density parameter.

### **3.2.6 Friability**

Most simulants are expected to be unconsolidated on the bulk scale and thus friability, defined as the tendency to reduce to finer particles under stress, is not applicable. Individual particles in a simulant or regolith such as breccias may be friable. Although friability and other measurements of mechanical strength are important considerations in simulant production, these properties of lunar regolith have not been measured adequately enough to simulate them.

### **3.2.7 Permeability**

Permeability is a function of the particle shape and size distribution and bulk density. It may not be uniquely constrained by these characteristics.

## **3.3 Grain Specific**

Size and shape are not defined by the 2005 workshop report. These concepts can only be given physical meaning by defining a specific method of measurement. Many of the measurement methods have physical meaning or are only applied to assemblies of particles.

### **3.3.1 Grain Size**

This is an explicit part of the FoM standard.

### **3.3.2 Grain Size Distribution**

This is an explicit part of the FoM standard.

### **3.3.3 Grain Shape**

This is an explicit part of the FoM standard.

### **3.3.4 Magnetic Grain Properties**

Magnetic properties derive from the mineralogy, grain or particle size, and environmental history of the particle. For example, heating above a material specific temperature will cause a radical change in magnetic response. Subsequent cooling will change it yet again. In lunar materials, particle composition should determine most of the magnetism of the bulk material, but

this is complicated by the presence of nanophase iron metal ( $n\text{Fe}^0$ ) in the lunar regolith. At this time,  $n\text{Fe}^0$  is normally considered as a distinct solid phase independent of the commonly present  $\text{Fe}^0$  derived from meteoritic sources. Nanophase  $\text{Fe}^0$  is present in the agglutinates and in vapor-deposited nanoscale rims on particles. As of now, the  $n\text{Fe}^0$  in the agglutinates can only be partially reproduced, and that is at significant cost. The rims cannot be reproduced.

The FoM incorporates the mineral phase  $\text{Fe}^0$ . This was done to address both the meteoritic derived iron and the  $n\text{Fe}^0$ . The FoM also explicitly incorporates the particle type agglutinate. It is concluded that when fully implemented, these two measures, with the other FoM characteristics, will reasonably cover the performance of lunar material and simulants. This is almost certainly true for first order and probably most second order measurements. It is acknowledged that this may not be the case for very high quality measurements due to the role of particle history. As there is so little applicable information of any kind on this topic for actual lunar material, inclusion of such a parameter in the current FoM would violate basic characteristics of a standard, being neither measurable nor known.

### **3.3.5 Grain Shape Distribution**

This is an explicit part of the FoM standard.

### **3.3.6 Electrostatic Charging**

This is not part of the FoM standard. There is little data on this parameter for lunar material. It is almost certainly dominated by the composition and size of the particles, which is addressed by the particle type and size FoM. The limitation on this is the effect of the vapor-deposited rims.

## **3.4 Chemical**

### **3.4.1 Glass Composition**

Glass composition is important to many applications like in situ resource utilization (ISRU) and fabrication. Theoretically, the particle type FoM measures abundance and composition of particles. The diverse populations of glass compositions in lunar regolith pose a unique problem for evaluation. In the first FoM software release, only glass abundance is included in the algorithm, though there are entry spaces for subclasses of glass. This allows the user to define populations of glass (basaltic glass, Ti-rich basaltic glass, etc.) in the reference and simulant. Future revisions to the FoM software will include a routine to compare the chemical composition of glass in the materials and the abundance of the glass.

### **3.4.2 Bulk Chemistry**

This is an implicit part of the FoM standard. If the composition of the particles is known, the bulk chemistry of the particles is known. The limitation to this is a question of precision. The standardized list of minerals does not cover all possible minerals, nor does it attempt to specify

glass composition other than to restrict it by normative mineralogy. The minor element (<1 wt. %) and trace element (<0.1 wt. %) chemistry of a material is less well determined by particle type composition, except for cases like phosphorous (P), which is specifically addressed by reporting the modal percent of phosphates—the only minerals in which it is likely to occur.

### **3.4.3 Reactivity as Volatile/Soluble Minerals**

Although the meaning of this entry is not entirely clear in the 2005 workshop document, it seems to refer to volatile (e.g., hydroxyl (OH), water (H<sub>2</sub>O), and carbon dioxide (CO<sub>2</sub>))-bearing materials and halogen (fluorine (F), chlorine (Cl), bromine (Br), and iodine (I))-bearing materials.

**3.4.3.1 Volatile-Bearing Materials.** The presence of volatile-bearing materials in a simulant invokes a penalty to the composition FoM because correlative materials do not occur in lunar regolith. Furthermore, in revision 1 of the FoM software, these volatile-bearing minerals will populate their own subclass under the nonlunar minerals heading, and their presence will be weighted more than other nonlunar minerals due to their adverse affects on many ISRU processes.

**3.4.3.2 Halogen-Bearing Materials.** For halogen-bearing materials, the primary F- and Cl-bearing mineral in lunar regolith is the phosphate apatite. There is an entry for fluoroapatite on the FoM composition sheet; therefore, its presence, or lack thereof, will be assessed.

### **3.4.5 Surface Reactivity (Including Damage)**

Surface reactivity is dependent on particle type (for reasons of chemistry) and on surface area (see section 3.2.5 of this TM). It is also dependent on the activation of a particle surface, a variable condition determined by particle lattice damage, lack or presence of adsorbates, and other characteristics. No general, measurable parameter correlates to this condition. Furthermore, it would seem to be a dynamic condition that would be difficult to impart to a bulk material by the manufacturer.

## **3.5 Mineralogical**

### **3.5.1 Mineralogical Composition as Function of Grain Size**

This is an explicit part of the FoM standard.

### **3.5.2 Modal Mineralogical Composition**

This is an explicit part of the FoM standard.

### **3.5.3 Soil Texture**

This is not defined and has many, many meanings. Some of the possible meanings are directly related to size and shape distribution and to material density.

## **3.6 Multicategory**

### **3.6.1 Implanted Solar Particles**

This is not addressed by the FoM as of this date. It is not considered practical or useful to add during simulant production. Reproduction of the process or result would likely be very expensive, and it seems best for the investigator to carry out treatment to replicate this property. This may change in the future.

### **3.6.2 Agglutinates With Nanophase Iron**

The particle type FoM can address the presence of  $n\text{Fe}^0$  in the agglutinates. In version 1 of the software, data on the distributions of agglutinates are required. A subclass could be added of those agglutinates containing  $n\text{Fe}^0$  after this property is defined in the requirements document.

#### **4. CONCLUSION**

The FoM is considered to be a work in progress, both conceptually and in terms of algorithm and software development. It provides a reasonable and practical means to compare materials by addressing fundamental, inherent, measurable characteristics.



## REFERENCES

1. Sibille, L.; Carpenter, P.; Schlagheck, R.; and French, R.A.: “Lunar Regolith Simulant Materials: Recommendations for Standardization, Production, and Usage,” *NASA/TP—2006–214605*, 118 p, 2006.
2. Rickman, D.; Hoelzer, H.; Carpenter, P.; et al.: “A Quantitative Method for Evaluating Regolith Simulants,” *Space Technology And Applications International Forum*, Albuquerque, NM, February 11–15, 2007.
3. Rickman, D.: *Lunar Regolith Simulant Requirements, Pre-Decisional Draft*, MSFC–RQMT–3503, 90 p, August 31, 2006.
4. Houck, K.J.: “Modal Petrology of Six Soils From Apollo 16 Double Drive Tube 64002,” Proceedings of the 13th Lunar and Planetary Science Conference, Part 1, *J. Geophys. Res.*, Vol. 87, Sup., pp. A210–A220, 1982.
5. Graf, J.C.: *Lunar Grain Size Catalog*, NASA Reference Publication 1265, 464 p, 1993.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188		
<p>The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operation and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.</p> <p><b>PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.</b></p>					
1. REPORT DATE (DD-MM-YYYY) 01-09-2010		2. REPORT TYPE Technical Memorandum		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE  Figure of Merit Characteristics Compared to Engineering Parameters			5a. CONTRACT NUMBER		
			5b. GRANT NUMBER		
			5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S)  C.M. Schrader,* and D.L. Rickman			5d. PROJECT NUMBER		
			5e. TASK NUMBER		
			5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) George C. Marshall Space Flight Center Marshall Space Flight Center, AL 35812			8. PERFORMING ORGANIZATION REPORT NUMBER  M-1292		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546-0001			10. SPONSORING/MONITOR'S ACRONYM(S) NASA		
			11. SPONSORING/MONITORING REPORT NUMBER NASA/TM-2010-216443		
12. DISTRIBUTION/AVAILABILITY STATEMENT Unclassified-Unlimited Subject Category 91 Availability: NASA CASI (443-757-5802)					
13. SUPPLEMENTARY NOTES Prepared by the Earth Sciences Office *BAE Systems, Huntsville, Alabama					
14. ABSTRACT A workshop held in 2005 defined a large number of parameters of interest for users of lunar simulants. The need for formal requirements and standards in the manufacture and use of simulants necessitates certain features of measurements. They must be definable, measureable, useful, and primary rather than derived. There are also certain features that must be avoided. Analysis of the total parameter list led to the realization that almost all of the parameters could be tightly constrained, though not predicted, if only four properties were measured: Particle composition, particle size distribution, particle shape distribution, and bulk density. These four are collectively referred to as figures of merit (FoMs). An evaluation of how each of the parameters identified in 2005 is controlled by the four FoMs is given.					
15. SUBJECT TERMS lunar simulant, figure of merit, engineering, particle composition, particle shape, particle size, bulk density					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON
a. REPORT	b. ABSTRACT	c. THIS PAGE			STI Help Desk at email: help@sti.nasa.gov
U	U	U	UU	24	19b. TELEPHONE NUMBER (Include area code) STI Help Desk at: 443-757-5802



National Aeronautics and

Space Administration

IS20

**George C. Marshall Space Flight Center**

Marshall Space Flight Center, Alabama

35812